

## GRAVIHEL PUR HS 452 – 005 VISOKO SJAJNI

### Upotreba:

Visokokvalitetni pokrivni premaz s visokom zaštitom od vremena, mehaničkom, kemijskom i UV zaštitom, također prikladan za bojanje automobila.

Preporučen omjer vezivne osnove (veziva) i pastama je 65:35.

### Podloga:

GRAVIHEL EPOXY PRIMER 50 RAL

### Tip:

2K akrilno vezivo

### Izgled:

visoki sjaj

### Dobavna viskoznost:

DIN4 /20°C = 120 - 130 s

### Gustoća komponente A:

0,997 kg/l

### Suha tvar A+B u dobavnom obliku:

Volumenski: 60 %

Težinski: 63 %

### VOC:

2004/42/IIIB(d)(420)418

VOC spreman za uporabu (g/l)= max.418

### Teoretska izdašnost:

10 m<sup>2</sup>/lit.

### Nijansa:

GRAVIHEL COLOR TOOLS



2 : 1 +10%

GraviHEL 2K PUR HS UTVRĐIVAČ MF  
GraviHEL 2K PUR RAZRJEĐIVAČ MF

Zapreminsko miješanje

Pot life / 20°C =1,5h



20 - 22 sek.


DIN 53211  $\Phi$ 4 /20°C



1,3 mm

2 – 3 bara (ovisno o vrsti pištolja)

1 - 2x = 40 - 60 $\mu$ m



između slojeva: 10 min. /20°C



Suh na prašinu /20°= 25 min.

Suh na dodir /20°C = 12 – 14 h

60°C = 30 min.



10 - 15 min. kratki valovi



Skladištenje:

2 leti