

GRAVIHEL PUR SINGLE COAT 800 DTG 800 – 011 DEEP MATT

Use:

Two-component single-layer coating intended for direct application on glass. It is intended for a wide variety of applications where we want to paint the back side of the glass surfaces: kitchen and bathroom glass surfaces, glass and partitions ...

The coating can be made in a wide variety, both uni and effective shades. The recommended ratio between the base (binder) and pastes is 80:20. However, for additional requirements on the covering power the amount of pastes can be increased to 75:25

Type of product:

Acrylic resin

Appearance:

Deep matt

Delivery viscosity:

Thixotropic

Density of component A:

1,4 – 1,565 kg/l

Solid Content:

By volume: 45%

By weight: 76%

VOC:

2004/42/IIIB(e)(840)490

VOC ready to use (g/l)= max.490

Theoretical yield:

4 - 5 m² /lit.

Color shades:

GRAVIHEL COLOR TOOLS



4:1 + 25%

**GRAVIHEL 2K SINGLE COAT
HARDENER
GRAVIHEL THINNER ESS**

Volume mixing

Pot life / 20°C = 4h



18 - 20 sek.


DIN 53211 ϕ 4 /20°C



1,3 – 1,7 mm

2 – 3 bare (depending on type of gun)

2x = 60 - 70 μ m



Between coats: 10 min. /20°C



Powder dry /20°= 30 min.

Dry to touch/ 20°C = 5h

60°C = 30 min.



8 – 12 min. in the short-wave



Thinner is not needed



Shelf life:

2 years